

Product data sheet

SIGA-Majcoat® SOB / Majcoat®



Updated on: 30/12/2016

Reference standard: EN 13859-1 / -2



Distributor: SIGA

Type of application: breathable membrane with/without integrated dual adhesive zone, for durably rainproof and windtight building envelopes for pitched roofs and facades

Instructions: see manual

Palett: 30 rolls bound in layers

Construction: 3-layered; functional layer protected on both sides with PP nonwoven.

Characteristics:

		Standards	Units	Values
Dimensions	length width straightness	EN 1848-2 EN 1848-2 EN 1848-2	m m -	50 1.5 passed
Total weight Thickness		EN 1849-2 EN 1849-2	g/m ² mm	190 0.6
Resistance to tearing (nail shank)*	lengthwise crosswise	EN 12310-1	N	220 240
Tensile properties Tensile strength*	lengthwise crosswise	EN 12311-2	N/50 mm	360 270
Tensile properties Elongation*	lengthwise crosswise	EN 12311-2	%	70 80
Air layer thickness equivalent to diffusion s_d Water vapour permeability		EN ISO 12572 EN ISO 12572	m g/(m ² ·d)	0.1 190
Resistance to water penetration		EN 1928	-	W1
Fire classification		EN 13501-1	class	E
Temperature resistance			°C	-40 °C to +80 °C

*average